

# EASY ON, EASY OFF ACCESS · WILL NOT SUPPORT COMBUSTION EASILY FITS AROUND ODD-SHAPED CONNECTORS

Flame Retardant Flexo® Wrap (FWF) provides the same hook and loop wire management flexibility as our standard Flexo® Wrap along with the added safety feature of an organic flame inhibitor to provide an additional level of security. FWF is a safe, economical solution for a wide range of cable management applications where moderate levels of flame protection are needed. Flexo® Wrap FR is designed for quick and easy management of wire, cable and hose assemblies. Just separate the hook and loop fasteners along the edge of the material and slip the entire length of FW around or under your harness or component assembly. The wide expandability range allows FW to easily fit around an odd-shaped connectors and gently constrict around the diameter of your wires. When the FW is in place, simply seal the hook and loop along the edges.

## **SIZING CHART**

Nominal			Hook	Recommended	*Put-Ups		Available	Lbs/
Siz		Part #	& Loop Width	Application Diameter	М	L	Colors	100'
1/2	"	FWF0.50TB	1⁄4″	1⁄2″	20'	100'	1	1.30
3⁄4	"	FWF0.75TB	<sup>5</sup> /8″	1⁄2″	15'	100'	1	1.80
11/2	. " 1	FWF1.25TB	<sup>5</sup> /8″	1″	12'	100'	1	2.30
2'	"	FWF2.00TB	<sup>5</sup> /8"	1 ¼"	10'	100'	1	3.20
21/2	2″	FXF2.50TB	<sup>5</sup> /8"	2"	10'	100'	1	3.75

\*Put-Ups: "M" = Shop Spool and "L" = Bulk Spool



## **FEATURES**

Material	Polyethylene Terephthalate
Grade	FWF
Monofilament Diameter	.010"
Drawing Number	TF001FWF-WD
Cutting	Hot Knife

## COLORS



## CERTIFICATIONS







#### **ABRASION**

Abrasion Resistance	MEDIUM
Abrasion Test Machine	Taber 5150
Abrasion Test Wheel	Calibrase H-18
Abrasion Test Load	500g
Room Temperature	70°F
Humidity	63%
Slight Scuffing & One Broken Filament	300 Test Cycles
One Dozen Filaments Broken	500 Test Cycles
Material Destroyed	900 Test Cycles
Pre-Test Weight	3,772.7 mg
Post-Test Weight	3,391.1 mg
Test End Loss Of Mass Point Of Destruction	381.6 mg

#### **PHYSICAL PROPERTIES**

Monofilament Diameter (ASTM D-204)	.010"
Flammability Rating (FMVSS-302 Approved)	VW-1
Recommended Cutting	Hot Knife
Colors	1
Wall Thickness	.025"
Tensile Strength (Yarn) (ASTM D-2256 Lbs)	5
Specific Gravity (ASTM D-792)	1.38
Moisture Absorption % (ASTM D-570)	.12
Hard Vacuum Data (ASTM E-595 at 10-5 torr)	NA
TML	.19
CVCM	.04
WVR	.06
Smoke D-Max (ASTM E-662)	275
Outgassing	Medium
Oxygen Index (ASTM D-2863)	31

## **FLAMMABILITY**

### **OPERATING TEMPERATURES**

Melt Point (ASTM D-2117)	482°F / 250°C
Maximum Continuous	257°F / 125°C
Minimum Continuous	-94°F / -70°C

#### CHEMICAL RESISTANCE

1=No Effect 2=Little Effect 3=Affected	4=More Affected 5=Severely Affected
Aromatic Solvents	2
Aliphatic Solvents	1
Chlorinated Solvents	3
Weak Bases	1
Salts	1
Strong Bases	2
Salt Water (0-S-1926)	1
Hydraulic Fluid (MIL-H-5606)	1
Lube Oil (MIL-L-7808)	1
De-Icing Fluid (MIL-A-8243)	1
Strong Acids	3
Strong Oxidants	2
Esters/Ketones	2
UV Light	1
Petroleum	1
Fungus (ASTM G-21)	1
Halogen Free	Yes
RoHS	Yes
SVHC	None

#### www.TECHFLEX.com

104 Demarest Road • Sparta, NJ 07871 • 1 (833) SLEEVING • (973) 300-9242 • fax: (973) 300-9409

© 2023 Techflex® - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex® is strictly forbidden. Techflex® product names and logos are registered trademarks of Techflex®, unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable. Techflex® makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex's only obligations are those in standard terms of sale for these products and Techflex® will not be liable for any consequential or other damages arising disclaims any liability in connection with their use. Techflex's<sup>®</sup> only obligations are those in standard terms of sale for these products and recimex<sup>®</sup> with not be nable for any consequential or other damages and gradient or the suitability of these products for their unique and specific applications. due to misuse of these products or typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications. 08-01-23