

0833202

https://www.phoenixcontact.com/us/products/0833202

Please be informed that the data shown in this PDF document is generated from our online catalog. Please find the complete data in the user documentation. Our general terms of use for downloads are valid.



Shrink sleeve, Roll, white, unlabeled, can be labeled with: THERMOMARK E.300 (D)/600 (D), THERMOMARK ROLLMASTER 300/600, THERMOMARK ROLL X1, THERMOMARK ROLL, THERMOMARK ROLL 2.0, THERMOMARK X1.2, cable diameter range: 9.5 ... 19.1 mm, unperforated, mounting type: slide-on, Number of individual labels: 500, text field height: 30 mm, text field width: 60 mm

Product description

Due to their ladder-style format, the preassembled shrink sleeves in the WMS-2 HF... product family provide a good overview and facilitate quick use. After the printing and applying process, you have the option of shrinking the marked shrink sleeves by applying heat manually and thus fixing them on the cable/wire.

Your advantages

- · Permanent and captive identification of single-core wires, wires, cables, pneumatic hoses, and other cylindrical objects
- · Ladder style design: For a good overview and to facilitate quick use, the sleeves are preassembled in cut lengths: 15 mm, 30 mm, or 60 mm
- · As an option, the sleeves can be shrunk by applying heat manually to fix the sleeve in position
- · High diameter coverage with a shrink ratio of 2:1
- · Widely used and proven worldwide in the railway industry

Commercial data

Item number	0833202
Packing unit	1 pc
Minimum order quantity	1 pc
Sales key	BG14
Product key	BG2216
Catalog page	Page 221 (C-3-2019)
GTIN	4055626044491
Weight per piece (including packing)	1,667 g
Weight per piece (excluding packing)	1,667 g
Customs tariff number	39173200
Country of origin	DK



0833202

https://www.phoenixcontact.com/us/products/0833202

Technical data

Notes

Material information	The specified minimum wire diameter of the shrink sleeve refers to its use as a marking material and does not guarantee any insulation characteristics once shrunk.
	Depending on the processed material batch, as well as the storage and processing conditions, the maximum insertable wire diameter may be reduced.

Product properties

Product type	Shrink sleeve	
Area of application	Railway industry	
Туре	Shrink sleeve	
Marking		
Number of individual labels	500	

1

Thermal transfer for rolls

Dimensions

Width	30 mm
Length	60 mm

External dimensions

Number of individual labels per row

Identification technology

Outside diameter	9.5 mm 19.1 mm
Text field	

Text field width	60 mm
Text field height	30 mm

Material specifications

Color	white (RAL 9010)
Material	Polyolefine
Base element material	polyolefine
Shrink rate	2:1
Fire protection for rail vehicles (DIN EN 45545-2) R22	HL 1 - HL 3
Fire protection for rail vehicles (DIN EN 45545-2) R23	HL 1 - HL 3
Fire protection for rail vehicles (DIN EN 45545-2) R24	HL 1 - HL 3
Components	halogen-free
Shrink temperature	> 90 °C

Cable/line

Environmental and real-life conditions



0833202

https://www.phoenixcontact.com/us/products/0833202

Result	Test passed
st for substances that would hinder coating with paint or varnish	
Result	Test passed
ratch test for the determining scratch resistance	
Specification	DIN EN ISO 1518-1:2019-10 (following)
Requirements	≥ 5 N
Result	Test passed
esafilm test	
Specification	DIN EN ISO 2409:2013 (following)
Result	Test passed
	,
/ resistance Specification	ISO 4892-2:2013-03 (following)
Result	Test passed
Test duration	96 h
Tool dardion	
emperature resistance	
Specification	ANSI/UL 969-2018:03 (following)
Test duration	240 h
Rating 125 °C (150 °C)	Test passed
pe resistance of inscriptions	
Specification	DIN EN 61010-1 (VDE 0411-1):2011-07
	DIN EN 62208 (VDE 0660-511):2012-06 (in parts)
Isopropyl [CAS No. 67-63-0]	Test passed
n-Hexane [CAS No. 110-54-3]	Test passed
Water + Petroleum ether [CAS No. 64742-82-1]	Test passed
Sodium hydroxide 0.1 mol/l [CAS No. 1310-73-2]	Test passed
Ethanol (99 %) [CAS No. 64-17-5]	Test passed
Specification	ISO 175:2010 (following)
	ISO 175:2010 (following) 168 h
Specification Test duration Sodium hydroxide 0.1 mol/l [CAS No. 1310-73-2]	
Test duration Sodium hydroxide 0.1 mol/l	168 h
Test duration Sodium hydroxide 0.1 mol/l [CAS No. 1310-73-2] Ethanol (99 %)	168 h Test passed
Test duration Sodium hydroxide 0.1 mol/l [CAS No. 1310-73-2] Ethanol (99 %) [CAS No. 64-17-5] Acetone (99 %)	168 h Test passed Test passed



0833202

https://www.phoenixcontact.com/us/products/0833202

IRM 902	Test passed
Testing in a condensation changing climate in the presence of sulfur of	dioxide
Specification	DIN 50018:2013-05
Result	Test passed
Climate level	AHT 1.0 S
Cycles	2
Salt spray test	
Specification	DIN EN 60068-2-11:2000-02
Result	Test passed
Test duration	96 h
Ambient conditions	
Ambient temperature (operation)	-30 °C 105 °C
Recommended ambient temperature (storage/transport)	10 °C 25 °C
Recommended humidity (storage/transport)	45 % 55 % (Storage in a dry and dark place in the original packaging is recommended)
Shelf life	2 years
andards and regulations	
Wipe resistance	DIN EN 61010-1 (VDE 0411-1)
Standards	
Standards/regulations	EN 45545-2
ounting	
Mounting type	slide-on



0833202

https://www.phoenixcontact.com/us/products/0833202

Classifications

	ECLASS-13.0	27281102	
E٦	TIM		
	ETIM 9.0	EC001530	
UNSPSC			
	UNSPSC 21.0	39131500	



0833202

https://www.phoenixcontact.com/us/products/0833202

Environmental product compliance

EU RoHS

Fulfills EU RoHS substance requirements	Yes, No exemptions
EU REACH SVHC	
EU REACH SVHC REACH candidate substance (CAS No.)	No substance above 0.1 wt%

Phoenix Contact 2025 © - all rights reserved https://www.phoenixcontact.com

Phoenix Contact USA 586 Fulling Mill Road Middletown, PA 17057, United States (+717) 944-1300 info@phoenixcon.com